



TECHNICAL DATA SHEET

Product Code	DWBC-050-C														
Product Description	A high-quality textured coating designed to enhance and protect exterior and interior walls. Formulated with high-grade fillers and acrylic binders, it offers excellent durability, water resistance, and weather protection. Prostar DecoPlast's sandy texture provides a modern aesthetic and conceals surface imperfections														
Intended Uses	- Interior or Exterior walls - Applied on plastered or painted walls. - Suitable for application to suitably primed cement plaster, concrete, brickwork, fibre-cement, breeze blocks														
Features & Benefits	- Allows for vertical or swirl-textured finishes - Enables decorative patterning with consistent texture - Suitable for both interior and exterior use - Can be applied over previously painted or newly plastered surfaces - Excellent adhesion to properly prepared substrates - Hides surface imperfections														
Product Information	<table> <tr> <td>Appearance:</td><td>1.0mm or 2.0m Scratch available.</td></tr> <tr> <td>Colours:</td><td>Soft Grey, Charcoal, and other ready mixed colours</td></tr> <tr> <td>Solids:</td><td>Approx.58 – 62 % by weight</td></tr> <tr> <td>Density:</td><td>Approx. 1.6 g/l</td></tr> <tr> <td>Spreading Rate:</td><td>Approx. 16 – 20 m² per 28kg bucket</td></tr> <tr> <td>Flash Point:</td><td>Non – Flammable</td></tr> <tr> <td>Binder Type:</td><td>Acrylic Emulsion</td></tr> </table> This product is manufactured under strict SABS ISO 9001 : 2015 quality standards.	Appearance:	1.0mm or 2.0m Scratch available.	Colours:	Soft Grey, Charcoal, and other ready mixed colours	Solids:	Approx.58 – 62 % by weight	Density:	Approx. 1.6 g/l	Spreading Rate:	Approx. 16 – 20 m ² per 28kg bucket	Flash Point:	Non – Flammable	Binder Type:	Acrylic Emulsion
Appearance:	1.0mm or 2.0m Scratch available.														
Colours:	Soft Grey, Charcoal, and other ready mixed colours														
Solids:	Approx.58 – 62 % by weight														
Density:	Approx. 1.6 g/l														
Spreading Rate:	Approx. 16 – 20 m ² per 28kg bucket														
Flash Point:	Non – Flammable														
Binder Type:	Acrylic Emulsion														
Application Details	<table> <tr> <td>Mixing:</td><td>Stir thoroughly and occasionally during use.</td></tr> <tr> <td>Method:</td><td>Ready for use. Use a steel trowel and apply as a skim coat then float with a plastic or wooden trowel.</td></tr> <tr> <td>Thinning:</td><td>Not Recommended</td></tr> <tr> <td>Cleaning:</td><td>Water clean-up</td></tr> <tr> <td>Drying Time:</td><td>Surface dry: 2 Hours Hard dry: 12 - 14 hours Depending on temperature and humidity.</td></tr> <tr> <td>Cleaning of Equipment:</td><td>After use, remove as much product as possible, and then clean immediately with water.</td></tr> </table>	Mixing:	Stir thoroughly and occasionally during use.	Method:	Ready for use. Use a steel trowel and apply as a skim coat then float with a plastic or wooden trowel.	Thinning:	Not Recommended	Cleaning:	Water clean-up	Drying Time:	Surface dry: 2 Hours Hard dry: 12 - 14 hours Depending on temperature and humidity.	Cleaning of Equipment:	After use, remove as much product as possible, and then clean immediately with water.		
Mixing:	Stir thoroughly and occasionally during use.														
Method:	Ready for use. Use a steel trowel and apply as a skim coat then float with a plastic or wooden trowel.														
Thinning:	Not Recommended														
Cleaning:	Water clean-up														
Drying Time:	Surface dry: 2 Hours Hard dry: 12 - 14 hours Depending on temperature and humidity.														
Cleaning of Equipment:	After use, remove as much product as possible, and then clean immediately with water.														
Surface Preparation	All surfaces must be sound, dry, and free of dust, grease, oil, or other contaminants that could impair adhesion. New plaster should be allowed to cure fully (minimum 21–28 days) before application. Moisture levels should be below 15% moisture. NEW SURFACES: Prime with the Prostar Plaster Primerseal 4 in 1 Alkali Resistant and allow 24 hours recommended drying time before applying topcoat. Apply 1 coat of Prostar PureSatin / WeatherCoat in desired colour as a basecoat. PREVIOUSLY PAINTED SURFACES – Good Condition: Clean surfaces with Prostar Sugar Soap Powder solution to remove Contaminants. Rinse with clean water to remove traces of Prostar Sugar Soap Powder. Spot prime bare surfaces with an appropriate primer. Poor Condition: Completely remove all loose and flaking paint. Remove contaminants by washing with Prostar Sugar Soap Powder. Rinse with clean water to remove traces of Prostar Sugar Soap Powder and allow to dry. Spot prime bare surfaces with an appropriate primer. Chalky Surfaces: Remove chalky surfaces using Prostar Sugar Soap Powder by scrubbing. Rinse with clean water and allow to dry. Apply a coat of Prostar Plaster Primerseal 4 in 1 Alkali Resistant. Mouldy Surfaces: To kill algae growth, scrub surfaces with Prostar Anti-Fungal Wash. Allow surfaces to react with the solution for a minimum of 30 minutes. Rinse with clean water and allow to dry. Apply a coat of Prostar Plaster Primerseal 4 in 1 Alkali Resistant														



TECHNICAL DATA SHEET

- For best results, apply one coat of a basecoat or Topcoat in a similar colour as the selected **Prostar DecoPlast**. This helps enhance colour uniformity and coverage.
- Apply **Prostar DecoPlast** using a steel trowel, spreading the product evenly across the surface.
- Once the material begins to set, use a plastic float to create the desired finish: Swirl, Vertical, Horizontal or Angled.
- Work in continuous sections to maintain a uniform texture.
- Avoid application in direct sunlight or on hot surfaces to prevent premature drying.

Surface Preparation



Swirl



Vertical



Angled



Horizontal

Precautions

- Do not apply during inclement of extreme weather conditions:
 - wet, below 10°C or above 35°C
 - Relative humidity above 80 %
 - Temperature Lower than 3°C of dew point
- To ensure that colours on a project are consistent check that batch numbers and product codes are the same.

Tinting Protocol

- To ensure that the colour on a project is consistent, check that batch numbers and product codes are the same.
- Minimum order quantity for tinting is 8 x 28kg of paint.

Colour Disclaimer: Colours shown on our colour cards, website, and printed materials may vary slightly from the actual paint colour due to differences in lighting, surface texture, application & preparation method, product sheen and texture as well as individual monitor and printer settings. We strongly recommend testing a sample on your intended surface before making your final selection. Test pots and colour swatches are available in-store for this purpose. For best colour and sheen consistency, it is advisable to use containers of the same batch number or to finish in a corner before starting a new corner. For accurate colour representation, all substrates must be properly primed and white before any paint is applied. Painting over non-white surfaces may alter the final appearance of the colour and result in discrepancies from the intended shade.

Safety Precautions

- Keep out of reach of children.
- If product is ingested seek immediate medical advice.
- In case of eye contact seek medical attention.
- Always ensure good ventilation during and after application
- Do not smoke while painting.
- Wear a suitable dust mask if sanding.
- To avoid any risk of spillage, always transport in a secure upright position.

Storage Conditions

- Store in a cool, dry place away from direct sunlight or extreme cold.
- Open containers should not be stacked



TECHNICAL DATA SHEET

Disclaimer:

The recommendations contained herein are given in all good faith and are meant to guide the specify or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No Guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

DURBAN – MANUFACTURING

262 Inanda Road,
Springfield Park
Tel: 031 574 5376
From outside RSA: +27 31 574 5376

DURBAN – SALES

81 Moses Kotane Rd
Overport
Tel: 031 207 1133
From outside RSA: +27 31 207 1133

RICHARDS BAY - SALES

121/3 Dollar Drive, Shop 9
Richards Bay Central
Tel: 035 760 1166
From outside RSA: +27 35 760 1166

CAPE TOWN – SALES

Aster Industrial Park,
53 Socony Rd, Parow
Tel: 021 532 1535
From outside RSA: +27 21 532 1535

JOHANNESBURG - SALES

Unit 5, Criscon Park, 112 Richards Drive,
Halfway House, Midrand
Tel: 010 224 0180
From outside RSA: +27 10 224 0180

Email: Info@prostarpaints.co.za