



Product Code	CFA-011
Product Description	WallFix Crackfiller is a fine general purpose filler to fill in gaps or over surface imperfections.
Intended Uses	Can be applied to interior and exterior cement walls, plaster, gypsum boards and asbestos cement surfaces.
Features & Benefits	- It mixes easily with water to a lump-free and slump resistant paste which can be worked to a smooth finish. - It sands easily when dry to a perfectly smooth surface. - Can be over coated with enamel or water based coatings after priming.
Product Information	Appearance: Free flowing powder Colours: Off-white Solids: 100% Density: 2.38 (typical) This product is manufactured under strict SABS ISO 9001 : 2015 quality standards.
Application Details	Mixing: Add 1 part water to 2 parts of powder and mix thoroughly to a smooth uniform paste. Allow to stand for 5 minutes before use. Once mixed, the product remains workable for 60-90 minutes. Method: Putty knife, scraper. Cleaning: Water Conditions: Application is tested at 23°C in climate-controlled environment Working Time: Use within 1 hour after mixing Drying Time: Touch dry (5mm thickness): 30 min at 23°C Full cure: 24 hr Over coating: With Solvent based paint: 24 hr at 23°C With Water based paint: 4 hr at 23°C Spread rate: Approximately 2m²/kg when applied at 0.25mm thick.
Surface Preparation	- Open cracks to a "V" shape sufficiently to allow the filler to be pressed into position. - Remove paint in poor conditions by lightly sanding. - Make sure all surfaces are firm clean and dry before filling. - Paint nail heads inside cracks with Prostar Anti Corrosive Etch Primer. - Always use a clean container for mixing. - Mix only sufficient material for use within one hour. It is natural for the mixed material to thicken as it ages. Discard it when it becomes too thick for use – do not add water to thin. WallFix Crackfiller is not suitable for use in damp or wet conditions.
Precautions	- Do not apply during inclement of extreme weather conditions: - wet, below 10°C or above 35°C - Relative humidity above 80 % - Temperature Lower than 3°C of dew point - Do not apply directly to substrate without priming. - Do not wash for 7 days after painting.
Safety Precautions	- Keep out of reach of children. - If product is ingested seek immediate medical advice. - In case of eye contact seek medical attention. - Always ensure good ventilation during and after application - Ensure that product is stored in a cool dry. - Do not smoke while painting. - Wear a suitable dust mask if sanding. - To avoid any risk of spillage, always transport in a secure upright position.
Storage Conditions	- Store in a cool, dry place away from direct sunlight or extreme cold. - Open containers should not be stacked

**Disclaimer:**

The recommendations contained herein are given in all good faith and are meant to guide the specify or the user. They are based on results gained from our tests and experiences and are believed to be reliable. No Guarantee is implied by the recommendations contained herein since conditions of use, method of application and cleanliness of the substrate prior to painting are beyond our control.

NB: Technology may change with time necessitating changes to this Technical Data Sheet (TDS). It is the responsibility of the user to ensure that the latest TDS is being used.

DURBAN – MANUFACTURING

262 Inanda Road,
Springfield Park
Tel: 031 574 5376
From outside RSA: +27 31 574 5376

DURBAN – SALES

81 Moses Kotane Rd
Overport
Tel: 031 207 1133
From outside RSA: +27 31 207 1133

RICHARDS BAY - SALES

121/3 Dollar Drive, Shop 9
Richards bay Central
Tel: 035 760 1166
From outside RSA: +27 35 760 1166

CAPE TOWN – SALES

Aster Industrial Park,
53 Socony Rd, Parow
Tel: 021 532 1535
From outside RSA: +27 21 532 1535

JOHANNESBURG - SALES

Unit 5, Criscon Park, 112 Richards Drive,
Halfway House, Midrand
Tel: 010 224 0180
From outside RSA: +27 10 224 0180

Email: Info@prostarpaints.co.za